

Ash Quartz



Ash Quartz 0.4-0.9mm

Ash Quartz is a light coloured, naturally rounded quartz sand. It is washed, dried and graded.

Chemical Analysis

	%
SiO ₂	97.7 - 99.1
Fe ₂ O ₃	0.022 - 0.025
Al ₂ O ₃	0.526 - 1.325
CaO	0.006 - 0.010
MgO	0.015 - 0.046
Na ₂ O	0.035 - 0.073
K ₂ O	0.163 - 0.715


Physical Data

Particle Shape	Rounded
Colour	Light Grey
Specific Gravity g/cm ³	2.65
Hardness (Mohs)	7.0
Loss on Ignition	0.1%

Commodity Code

2505 100000

Particle Size Distribution



Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

All information is given in good faith but is indicative only and does not constitute a specification.

Boud Minerals Limited

West Bank, Sutton Bridge
Lincolnshire PE12 9UR, UK
Tel: +44 (0)1406 351988
Fax: +44 (0)1406 350897
Email: sales@boud.com
Web: www.boud.com

Boud Minerals AB

Håkantorpsvägen 109
SE-26391 Höganäs, Sweden
Tel: +46 42 333741
Fax: +46 42 333829
Email: sweden@boud.com
Web: www.boud.com

Ash Quartz 0.7-1.3mm

Ash Quartz is a light coloured, naturally rounded quartz sand. It is washed, dried and graded.

Chemical Analysis

	%
SiO ₂	97.7 - 99.1
Fe ₂ O ₃	0.022 - 0.025
Al ₂ O ₃	0.526 - 1.325
CaO	0.006 - 0.010
MgO	0.015 - 0.046
Na ₂ O	0.035 - 0.073
K ₂ O	0.163 - 0.715


Physical Data

Particle Shape	Rounded
Colour	Light Grey
Specific Gravity g/cm ³	2.65
Hardness (Mohs)	7.0
Loss on Ignition	0.1%

Commodity Code

2505 100000

Particle Size Distribution



Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

All information is given in good faith but is indicative only and does not constitute a specification.

Boud Minerals Limited

West Bank, Sutton Bridge
Lincolnshire PE12 9UR, UK
Tel: +44 (0)1406 351988
Fax: +44 (0)1406 350897
Email: sales@boud.com
Web: www.boud.com

Boud Minerals AB

Håkantorpsvägen 109
SE-26391 Höganäs, Sweden
Tel: +46 42 333741
Fax: +46 42 333829
Email: sweden@boud.com
Web: www.boud.com

Ash Quartz 0.8-1.8mm

Ash Quartz is a light coloured, naturally rounded quartz sand. It is washed, dried and graded.

Chemical Analysis

	%
SiO ₂	97.7 - 99.1
Fe ₂ O ₃	0.022 - 0.025
Al ₂ O ₃	0.526 - 1.325
CaO	0.006 - 0.010
MgO	0.015 - 0.046
Na ₂ O	0.035 - 0.073
K ₂ O	0.163 - 0.715


Physical Data

Particle Shape	Rounded
Colour	Light Grey
Specific Gravity g/cm ³	2.65
Hardness (Mohs)	7.0
Loss on Ignition	0.1%

Commodity Code

2505 100000

Particle Size Distribution



Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

All information is given in good faith but is indicative only and does not constitute a specification.

Boud Minerals Limited

West Bank, Sutton Bridge
Lincolnshire PE12 9UR, UK
Tel: +44 (0)1406 351988
Fax: +44 (0)1406 350897
Email: sales@boud.com
Web: www.boud.com

Boud Minerals AB

Håkantorpsvägen 109
SE-26391 Höganäs, Sweden
Tel: +46 42 333741
Fax: +46 42 333829
Email: sweden@boud.com
Web: www.boud.com

Ash Quartz 2.0-4.0mm

Ash Quartz is a light coloured, naturally rounded quartz gravel. It is washed, dried and graded.

Chemical Analysis

	%
SiO ₂	97.7 - 99.1
Fe ₂ O ₃	0.022 - 0.025
Al ₂ O ₃	0.526 - 1.325
CaO	0.006 - 0.010
MgO	0.015 - 0.046
Na ₂ O	0.035 - 0.073
K ₂ O	0.163 - 0.715


Physical Data

Particle Shape	Rounded
Colour	Light Grey
Specific Gravity g/cm ³	2.65
Hardness (Mohs)	7.0
Loss on Ignition	0.1%

Commodity Code

2505 10000

Particle Size Distribution



Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

All information is given in good faith but is indicative only and does not constitute a specification.

Boud Minerals Limited

West Bank, Sutton Bridge
Lincolnshire PE12 9UR, UK
Tel: +44 (0)1406 351988
Fax: +44 (0)1406 350897
Email: sales@boud.com
Web: www.boud.com

Boud Minerals AB

Håkantorpsvägen 109
SE-26391 Höganäs, Sweden
Tel: +46 42 333741
Fax: +46 42 333829
Email: sweden@boud.com
Web: www.boud.com

Ash Quartz 4.0-8.0mm

Ash Quartz is a light coloured, naturally rounded quartz gravel. It is washed, dried and graded.

Chemical Analysis

	%
SiO ₂	97.7 - 99.1
Fe ₂ O ₃	0.022 - 0.025
Al ₂ O ₃	0.526 - 1.325
CaO	0.006 - 0.010
MgO	0.015 - 0.046
Na ₂ O	0.035 - 0.073
K ₂ O	0.163 - 0.715


Physical Data

Particle Shape	Rounded
Colour	Light Grey
Specific Gravity g/cm ³	2.65
Hardness (Mohs)	7.0
Loss on Ignition	0.1%

Commodity Code

2505 10000

Particle Size Distribution



Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

All information is given in good faith but is indicative only and does not constitute a specification.

Boud Minerals Limited

West Bank, Sutton Bridge
Lincolnshire PE12 9UR, UK
Tel: +44 (0)1406 351988
Fax: +44 (0)1406 350897
Email: sales@boud.com
Web: www.boud.com

Boud Minerals AB

Håkantorpsvägen 109
SE-26391 Höganäs, Sweden
Tel: +46 42 333741
Fax: +46 42 333829
Email: sweden@boud.com
Web: www.boud.com

Boud

Minerals

Contact us

Call

UK: +44 (0)1406 351988

Sweden: +46 42 333741

Fax

UK: +44 (0)1406 350897

Sweden: +46 42 333829

Email

UK: sales@boud.com

Sweden: sweden@boud.com

Website

www.boud.com

Download the

Boud Minerals App



Boud Minerals Limited

*West Bank, Sutton Bridge
Lincolnshire PE12 9UR
UK*

Boud Minerals AB

*Håkantorpsvägen 109
SE-26391 Höganäs
Sweden*