

Colorfalt

Non-dusting, free-flowing pigment masterbatch that disperses readily in bitumen systems

Typical Properties	
Pigment	Red Iron Oxide
Pigment Content	Ca. 80%
Carrier	E.V.A.
Granule Shape	Cylindrical
Granule Size (average)	3mm x 1mm
Melting Point	90 - 120°C

Characteristics	Colorfalt V Red
Light Fastness (1% dosage measured on the Blue Wool Scale, DIN 53387 - 2 - E; 500 hours)	8
Weather Fastness (1% dosage measured on the ISO Grey Scale, DIN 53387 - 1A -X; 3000 hours)	4 - 5
Heat Resistance (1% dosage with a residence time of 5 min).	300°C (DPA - 003)

Packing

25 kilo bags on 1000 kilo pallets.

All information is given in good faith but no warranty is given that the goods will be suitable for any particular purpose and no liability is accepted for infringement of patents.

Issue 2 May 2012

Boud Minerals Limited

West Bank, Sutton Bridge, Lincolnshire PE12 9UR

Tel: +44 (0)1406 351988 Fax: +44 (0)1406 350897 Web: www.boud.com

Registered in England and Wales 1936377 VAT No. GB374 4151 56



ISO 9001 Certificate No. 3554