

# Crushed Flint



## Crushed Flint 0.3-0.5mm

Crushed Flint is a crushed mineral aggregate derived from blue flints. The flints are crushed in such a way to give a very angular surface.

### Chemical Analysis

	%
SiO <sub>2</sub>	93.6
Na <sub>2</sub> O / K <sub>2</sub> O / MgO	1.6
CaO	4.0
Fe <sub>2</sub> O <sub>3</sub>	0.2
Al <sub>2</sub> O <sub>3</sub>	0.6


### Physical Data

Particle Shape	Angular
Colour	Grey
Specific Gravity g/cm <sup>3</sup>	2.65
Bulk Density g/cm <sup>3</sup>	1.3-1.6
Hardness (Mohs)	7.0
Polished Stone Value	54
Water Absorption	0.7%

### Commodity Code

2517 101000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Crushed Flint 0.5-1.0mm

Crushed Flint is a crushed mineral aggregate derived from blue flints.

The flints are crushed in such a way to give a very angular surface.

### Chemical Analysis

	%
SiO <sub>2</sub>	93.6
Na <sub>2</sub> O / K <sub>2</sub> O / MgO	1.6
CaO	4.0
Fe <sub>2</sub> O <sub>3</sub>	0.2
Al <sub>2</sub> O <sub>3</sub>	0.6


### Physical Data

Particle Shape	Angular
Colour	Grey
Specific Gravity g/cm <sup>3</sup>	2.65
Bulk Density g/cm <sup>3</sup>	1.3-1.6
Hardness (Mohs)	7.0
Polished Stone Value	54
Water Absorption	0.7%

### Commodity Code

2517 101000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Crushed Flint 1.0-1.6mm

Crushed Flint is a crushed mineral aggregate derived from blue flints. The flints are crushed in such a way to give a very angular surface.

### Chemical Analysis

	%
SiO <sub>2</sub>	93.6
Na <sub>2</sub> O / K <sub>2</sub> O / MgO	1.6
CaO	4.0
Fe <sub>2</sub> O <sub>3</sub>	0.2
Al <sub>2</sub> O <sub>3</sub>	0.6


### Physical Data

Particle Shape	Angular
Colour	Grey
Specific Gravity g/cm <sup>3</sup>	2.65
Bulk Density g/cm <sup>3</sup>	1.3-1.6
Hardness (Mohs)	7.0
Polished Stone Value	54
Water Absorption	0.7%

### Commodity Code

2517 101000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Crushed Flint 1.0-3.0mm

Crushed Flint is a crushed mineral aggregate derived from blue flints. The flints are crushed in such a way to give a very angular surface.

### Chemical Analysis

	%
SiO <sub>2</sub>	93.6
Na <sub>2</sub> O / K <sub>2</sub> O / MgO	1.6
CaO	4.0
Fe <sub>2</sub> O <sub>3</sub>	0.2
Al <sub>2</sub> O <sub>3</sub>	0.6


### Physical Data

Particle Shape	Angular
Colour	Grey
Specific Gravity g/cm <sup>3</sup>	2.65
Bulk Density g/cm <sup>3</sup>	1.3-1.6
Hardness (Mohs)	7.0
Polished Stone Value	54
Water Absorption	0.7%

### Commodity Code

2517 101000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 February 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

# Boud

---

## Minerals

## Contact us

### Call

UK: +44 (0)1406 351988

Sweden: +46 42 333741

### Fax

UK: +44 (0)1406 350897

Sweden: +46 42 333829

### Email

UK: [sales@boud.com](mailto:sales@boud.com)

Sweden: [sweden@boud.com](mailto:sweden@boud.com)

### Website

[www.boud.com](http://www.boud.com)

Download the

Boud Minerals App



### Boud Minerals Limited

*West Bank, Sutton Bridge  
Lincolnshire PE12 9UR  
UK*

### Boud Minerals AB

*Håkantorpsvägen 109  
SE-26391 Höganäs  
Sweden*