

# Crushed Granite



# Crushed Granite

## Range



MicroBallast Red



MicroBallast Grey




MicroBallast Black




Criggion Green

## BML Pigmented Granite Colours




1418 Venetian Red



1553 Green



1563 Blue



1638 Red



## Micro Ballast Crushed Granite 0.4-1.0mm

A range of tightly screened crushed granite with a low dust content

### Chemical Analysis

	Red %	Grey %	Black %
SiO <sub>2</sub>	75.0	73.0	50.0
Al <sub>2</sub> O <sub>3</sub>	12.0	14.0	16.0
Fe <sub>2</sub> O <sub>3</sub>	2.5	1.8	11.0
CaO	1.0	2.3	10.0
MgO	0.3	0.6	7.2
Na <sub>2</sub> O	2.3	4.7	2.7
K <sub>2</sub> O	5.8	2.4	0.5
S	0.01	0.01	0.13
Soluble Iron	0.3	0.3	0.5


### Physical Data

	Red	Grey	Black
Specific Gravity g/cm <sup>3</sup>	2.6	2.7	2.9
Bulk Density g/cm <sup>3</sup>	1.3	1.4	1.5
Brittleness BS 812:3	16	15	7
Hardness (Mohs)	6	6	5-6
Loss on Ignition	0.7	0.6	1.0

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1050 kilos and bulk bags.

Not all grades may be available from stock.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Micro Ballast Crushed Granite 0.6-1.2mm

A range of tightly screened crushed granite with a low dust content

### Chemical Analysis

	Red %	Grey %	Black %
SiO <sub>2</sub>	75.0	73.0	50.0
Al <sub>2</sub> O <sub>3</sub>	12.0	14.0	16.0
Fe <sub>2</sub> O <sub>3</sub>	2.5	1.8	11.0
CaO	1.0	2.3	10.0
MgO	0.3	0.6	7.2
Na <sub>2</sub> O	2.3	4.7	2.7
K <sub>2</sub> O	5.8	2.4	0.5
S	0.01	0.01	0.13
Soluble Iron	0.3	0.3	0.5


### Physical Data

	Red	Grey	Black
Specific Gravity g/cm <sup>3</sup>	2.6	2.7	2.9
Bulk Density g/cm <sup>3</sup>	1.3	1.4	1.5
Brittleness BS 812:3	16	15	7
Hardness (Mohs)	6	6	5-6
Loss on Ignition	0.7	0.6	1.0

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1050 kilos and bulk bags.

Not all grades may be available from stock.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Micro Ballast Crushed Granite 1.2-1.8mm

A range of tightly screened crushed granite with a low dust content

### Chemical Analysis

	Red %	Grey %	Black %
SiO <sub>2</sub>	75.0	73.0	50.0
Al <sub>2</sub> O <sub>3</sub>	12.0	14.0	16.0
Fe <sub>2</sub> O <sub>3</sub>	2.5	1.8	11.0
CaO	1.0	2.3	10.0
MgO	0.3	0.6	7.2
Na <sub>2</sub> O	2.3	4.7	2.7
K <sub>2</sub> O	5.8	2.4	0.5
S	0.01	0.01	0.13
Soluble Iron	0.3	0.3	0.5


### Physical Data

	Red	Grey	Black
Specific Gravity g/cm <sup>3</sup>	2.6	2.7	2.9
Bulk Density g/cm <sup>3</sup>	1.3	1.4	1.5
Brittleness BS 812:3	16	15	7
Hardness (Mohs)	6	6	5-6
Loss on Ignition	0.7	0.6	1.0

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1050 kilos and bulk bags.

Not all grades may be available from stock.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Micro Ballast Crushed Granite 2.0-4.0mm

A range of tightly screened crushed granite with a low dust content

### Chemical Analysis

	Red %	Grey %	Black %
SiO <sub>2</sub>	75.0	73.0	50.0
Al <sub>2</sub> O <sub>3</sub>	12.0	14.0	16.0
Fe <sub>2</sub> O <sub>3</sub>	2.5	1.8	11.0
CaO	1.0	2.3	10.0
MgO	0.3	0.6	7.2
Na <sub>2</sub> O	2.3	4.7	2.7
K <sub>2</sub> O	5.8	2.4	0.5
S	0.01	0.01	0.13
Soluble Iron	0.3	0.3	0.5


### Physical Data

	Red	Grey	Black
Specific Gravity g/cm <sup>3</sup>	2.6	2.7	2.9
Bulk Density g/cm <sup>3</sup>	1.3	1.4	1.5
Brittleness BS 812:3	16	15	7
Hardness (Mohs)	6	6	5-6
Loss on Ignition	0.7	0.6	1.0

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1050 kilos and bulk bags.

Not all grades may be available from stock.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Micro Ballast Crushed Granite 5.0-8.0mm

A range of tightly screened crushed granite with a low dust content

### Chemical Analysis

	Red %	Grey %	Black %
SiO <sub>2</sub>	75.0	73.0	50.0
Al <sub>2</sub> O <sub>3</sub>	12.0	14.0	16.0
Fe <sub>2</sub> O <sub>3</sub>	2.5	1.8	11.0
CaO	1.0	2.3	10.0
MgO	0.3	0.6	7.2
Na <sub>2</sub> O	2.3	4.7	2.7
K <sub>2</sub> O	5.8	2.4	0.5
S	0.01	0.01	0.13
Soluble Iron	0.3	0.3	0.5


### Physical Data

	Red	Grey	Black
Specific Gravity g/cm <sup>3</sup>	2.6	2.7	2.9
Bulk Density g/cm <sup>3</sup>	1.3	1.4	1.5
Brittleness BS 812:3	16	15	7
Hardness (Mohs)	6	6	5-6
Loss on Ignition	0.7	0.6	1.0

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1050 kilos and bulk bags.

Not all grades may be available from stock.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Granite Criggion Green 2.0mm

A UK granite green / grey in colour.


### Physical Data

Particle Shape	Angular	Aggregate Abrasion Value %	7.3
Specific Gravity g/cm <sup>3</sup>	2.50-2.70	Impact Resistance AIV	13
Bulk Density g/cm <sup>3</sup>	1.30-1.50	Crushing Resistance	12
Polished Stone Value	61	Hardness (Mohs)	6.5

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 March 2016

All information is given in good faith but is indicative only and does not constitute a specification.

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com



## Granite Criggion Green 3.0mm

A UK granite green / grey in colour.


### Physical Data

Particle Shape	Angular	Aggregate Abrasion Value %	7.3
Specific Gravity g/cm <sup>3</sup>	2.50-2.70	Impact Resistance AIV	13
Bulk Density g/cm <sup>3</sup>	1.30-1.50	Crushing Resistance	12
Polished Stone Value	61	Hardness (Mohs)	6.5

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags

Issue 1 March 2016

All information is given in good faith but is indicative only and does not constitute a specification.

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com



## Granite Red 1.0 - 3.0mm

A UK crushed red granite


### Physical Data

Particle Shape	Angular	Impact Resistance AIV	12
Specific Gravity g/cm <sup>3</sup>	2.50 - 2.70	Crushing Resistance	21
Bulk Density g/cm <sup>3</sup>	1.30 - 1.50	Hardness (Mohs)	6.5
Polished Stone Value	55	10% Fines Value Kn	220
Aggregate Abrasion Value	1.4		

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags.

Issue 1 March 2016

All information is given in good faith but is indicative only and does not constitute a specification.

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Granite Red 2.0 - 5.0mm

A UK crushed red granite


### Physical Data

Particle Shape	Angular	Impact Resistance AIV	12
Specific Gravity g/cm <sup>3</sup>	2.50 - 2.70	Crushing Resistance	21
Bulk Density g/cm <sup>3</sup>	1.30 - 1.50	Hardness (Mohs)	6.5
Polished Stone Value	55	10% Fines Value Kn	220
Aggregate Abrasion Value	1.4		

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com



## Granite Grey 1.0 - 3.0mm

A UK crushed grey granite


### Physical Data

Particle Shape	Angular	Impact Resistance AIV	34
Specific Gravity g/cm <sup>3</sup>	2.50 - 2.70	Crushing Resistance	30
Bulk Density g/cm <sup>3</sup>	1.30 - 1.50	Hardness (Mohs)	6.5
Polished Stone Value	64	10% Fines Value Kn	110
Aggregate Abrasion Value	5.2		

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

## Granite Grey 2.0 - 5.0mm

A UK crushed grey granite


### Physical Data

Particle Shape	Angular	Impact Resistance AIV	34
Specific Gravity g/cm <sup>3</sup>	2.50 - 2.70	Crushing Resistance	30
Bulk Density g/cm <sup>3</sup>	1.30 - 1.50	Hardness (Mohs)	6.5
Polished Stone Value	64	10% Fines Value Kn	110
Aggregate Abrasion Value	5.2		

### Commodity Code

2517 490000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos and bulk bags.

Issue 1 March 2016

*All information is given in good faith but is indicative only and does not constitute a specification.*

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

# Boud

---

## Minerals

## Contact us

### Call

UK: +44 (0)1406 351988

Sweden: +46 42 333741

### Fax

UK: +44 (0)1406 350897

Sweden: +46 42 333829

### Email

UK: [sales@boud.com](mailto:sales@boud.com)

Sweden: [sweden@boud.com](mailto:sweden@boud.com)

### Website

[www.boud.com](http://www.boud.com)

Download the

Boud Minerals App



### Boud Minerals Limited

*West Bank, Sutton Bridge  
Lincolnshire PE12 9UR  
UK*

### Boud Minerals AB

*Håkantorpsvägen 109  
SE-26391 Höganäs  
Sweden*