

# Feldspar



## Feldspar FF20

Milled, crystalline anhydrous sodium potassium aluminium silicate

### Chemical Analysis

	%
SiO <sub>2</sub>	75.6
Al <sub>2</sub> O <sub>3</sub>	14.5
Na <sub>2</sub> O	4.8
K <sub>2</sub> O	4.2
CaO	0.2
Fe <sub>2</sub> O <sub>3</sub>	0.1


### Physical Data

Structure	Crystalline
Particle Shape	Nodular
Colour	White
Specific Gravity g/cm <sup>3</sup>	2.6
Bulk Density Loose g/cm <sup>3</sup>	0.8-1.3
Hardness (Mohs)	6.5
Brightness Index %	80.8
Refractive Index %	1.53
pH Aqueous Solution	9.8
Oil Absorption g/100g	32
Specific Surface Area M <sup>2</sup> /g	3.9
Median Particle Size Microns	6

### Commodity Code

2529 100000

### Particle Size Distribution



### Packing

25 kilo bags on pallets of 1000 kilos

Issue 6 May 2018

All information is given in good faith but is indicative only and does not constitute a specification.

### Boud Minerals Limited

West Bank, Sutton Bridge  
Lincolnshire PE12 9UR, UK  
Tel: +44 (0)1406 351988  
Fax: +44 (0)1406 350897  
Email: sales@boud.com  
Web: www.boud.com

### Boud Minerals AB

Håkantorpsvägen 109  
SE-26391 Höganäs, Sweden  
Tel: +46 42 333741  
Fax: +46 42 333829  
Email: sweden@boud.com  
Web: www.boud.com

